

# FIBERBUNDLE®

## LFB

### Description

FIBERBUNDLE is a flexible composite strength element consisting of E-glass and thermoplastic matrix, developed as a high modulus, non metallic, peripheral and central strength element for fiber optic and copper cables. Relative to standard LIGHTLINE®, FIBERBUNDLE offers high modulus performance without rigidity for greater cable flexibility.

### FIBERBUNDLE Physical Properties

Fiber Type	E-Glass
Resin Type	Thermoplastic
Approximate Fiber Percentage, by weight	83%
Approximate Resin Percentage, by weight	17%
Coefficient of Thermal Expansion (CTE)	5.9 X 10 <sup>-6</sup> C°
Standard Diameter Tolerances	+/- 8%
Maximum Lengths	60 km

### FIBERBUNDLE Mechanical Properties

Modulus of Elasticity	>50 GPa
Elongation at Break	>2.5%

### FIBERBUNDLE Standard Sizes

Product Code	Diameter		Minimum Elasticity		Tensile Strength	
	mm	in.	N %	lbs. %	N/mm <sup>2</sup>	PSI
LFB-160	1.60	0.062	756	170	710	103000
LFB-190	1.90	0.075	1112	250	710	103000

Custom sizes available upon request

NEPTCO warrants that its products will work in a manner consistent with the capabilities described in the data sheet. NEPTCO reserves the right to improve, enhance, and modify the features and specifications of these products. This warranty shall be void if the product has been tampered with or improperly used. Except for the express warranty and limited remedies described above, NEPTCO disclaims all other warranties including implied warranties. NEPTCO and its authorized agents shall have no other liability beyond the price of the product for damages to a purchaser, including consequential damages, occurring in connection with the use or performance of the product.

