



Core Wrap / Separator Tapes

NEPTAPE® FM100S

Construction: 0.00048" (12 μ) polyester film
0.00120" (30 μ) heat sealable copolymer

Description: Lighter grade heat sealable separator tape used to separate copper conductors, such as motor lead wires and a variety of other applications. Heat sealable copolymer bonds to PVC, polyethylene, and aluminum.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0015 inches	38 microns	ASTM D374
Yield	136.62 ft ² /lb 0.61 lbs/mft @ 1" wide	27.98 m ² /kg 0.36 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	9,300 psi	64 MPa	Calculated
Break Strength	14 lbs/in width	25 N/10mm width	ASTM D882
Elongation at Break	105%	105%	ASTM D882
Dielectric Strength of Film	2.8 kV	2.8 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	0.94 g/cm ³	Calculated
Max. Continuous Operating Temperature	175°F	80°C	Supplier Data
Sealing Temperature	210-240°F	100-115°C	NEPTCO TM-008
Splice Type	#4, max. 5/pad for < 22" OD or max. 6/pad for > 22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6 " Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.



The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

NEPTCO, Incorporated
Box 2323, 30 Hamlet Street
Pawtucket, RI 02861-0323 USA
TEL: 401-722-5500
FAX: 401-722-6378
www.neptco.com