



# AquaBlok® Water Blocking Tapes NEPTAPE® NGD325

**Construction:** Superabsorbent powder sandwiched between two layers of semi-conductive nonwoven polyester

**Description:** Semi-conductive water blocking tape typically used under the metallic shield of power cables.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0118 in. ± 0.0012 in.	0.30 mm ± .03 mm	ISO 9073-2
Mass per Unit Area	5.01 osy ± .42 osy	120 gsm ± 10 gsm	ISO 9073-1
Tensile at Break	17 lbs/in. width min.	30 N/10 mm width min.	ISO 9073-3
Elongation at Product Break	12%	12%	ISO 9073-3
Swell Speed (1 min)		8 mm	Cup & Ram Test
Swell Height (3 min)		12 mm	Cup & Ram Test
Surface Resistance		1,500 Ω per square	DIN IEC 167
Volume Resistance		1 x 10 <sup>6</sup> Ω·cm	DIN 54345
Short Term Stability	446°F	230°C	Supplier Data
Long Term Stability	194°F	90°C	IEC 216
Colors	Black		
Splice Type	#54, max. 5/pad for <22" OD or max. 6/pad for >22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 22"		
Standard Traverse Put-ups	Spool OD - 12" Traverse Length - 12"		



NEPTCO only warrants that its product will work in a manner consistent with the capabilities for which they were designed. This warranty shall be void if the product has been tampered with or improperly used.

Except for the express warranty and limited remedies described herein, NEPTCO DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.

The Buyer's remedies under the limited warranty stated above shall be limited to a return of the purchase price of the product. NEPTCO and its authorized agents shall not be liable for any other damages including consequential damages, incurred in connection with the use or performance of the product.

**NEPTCO, Incorporated**  
Box 2323, 30 Hamlet Street  
Pawtucket, RI 02861-0323 USA  
TEL: 401-722-5500  
FAX: 401-722-6378  
www.neptco.com